

PDA Training Course Extractables & Leachables

19-20 October 2023

POLYMERS 101

Dr. Piet Christiaens



OVERVIEW

1. Definition and classification
2. Types of polymers
3. Properties of polymers
4. On the origin of extractables species

OVERVIEW

- 1. Definition and classification**
2. Types of polymers
3. Properties of polymers
4. On the origin of extractables species

1. DEFINITION AND CLASSIFICATION

A **POLYMER** is a chemical compound or mixture of compounds consisting of **repeating structural units** created through a process of polymerization

Greek words:

πολύς (polus, meaning "many, much")

μέρος (meros, meaning "parts")

Refers to a molecule whose structure is composed of **multiple repeating units**


→ **High relative molecular mass** and associated properties

1. DEFINITION AND CLASSIFICATION


Origin of polymers

- **NATURAL POLYMERS** also exist in nature


- *Latex / natural rubber*
- *Starch*
- *Cellulose*
- *Pectine*
- *Silk / Wool*
- *DNA,...*




Repeating Isoprene units




Repeating D-Glucose units



Repeating Galacturonic acid units



Repeating units of amino acids



DNA


Most pharmaceutical applications are with **SYNTHETIC POLYMERS**

1. DEFINITION AND CLASSIFICATION

Examples of synthetic polymers





A small fraction are **INORGANIC POLYMERS**

Example: Siloxanes (PolyDiMethylSiloxanes; PDMS) (SILICONE)



However, most of the polymers are **ORGANIC POLYMERS**

Examples: polyethylene (PE), polypropylene (PP), ethylene vinyl acetate (EVA), polystyrene (PS), Isobutylene Isoprene Rubber (IIR rubber), nylon 6, nylon 6,6,...



1. DEFINITION AND CLASSIFICATION

THERMOPLASTIC

Polymers that soften when heated and become firm again when cooled

Examples: PS, LDPE, HDPE, PP, EVA, PTFE, PC,...




THERMOPLASTIC


“Entangled” polymer chains



Giving the **final form to a container/component** is based on these principles:



Extrusion



Injection Molding





1. DEFINITION AND CLASSIFICATION

THERMOSET

Polymers that soften when heated and molded subsequently BUT **decompose when reheated** (i.e. cannot be reformed after cooling)

Examples: Phenol formaldehyde resins, epoxy resins



Crosslinked polymer chains

Thermoset polymers are **typically “cross linked”** (irreversible chemical bonds formed during **curing** process)

Bakelite




1. DEFINITION AND CLASSIFICATION

ELASTOMER

Material with low degree of irreversible chemical cross-linking

Examples: rubbers and silicones



THERMOPLASTIC ELASTOMER (TPE)

Thermoplastic materials with elastomeric, rubbery-elastic properties generated by physical cross-linking points

TPE materials can be melted down again and thermoplastic processing is possible

Examples: styrene block copolymers (TPE-S: SBS, SEBS), polyolefin mixtures (TPE-O), thermoplastic polyurethanes (TPE-U), thermoplastic co-polyesters (TPE-E or TPC) and thermoplastic polyamides (TPE-A)

OVERVIEW

1. Definition and classification
- 2. Types of polymers**
3. Properties of polymers
4. On the origin of extractables species


2. TYPES OF POLYMERS

Organization of subunits

HOMOPOLYMER built from a sequence of identical monomers

Examples: PE, PP, PVC

A-A-A-A-A-A-A-A-A-A-A-A-A-A




COPOLYMER built from a sequence of two or more different monomers

Random copolymer

A-B-A-A-B-B-B-A-B-A-A-A-B


Example: Poly EVA



Regular copolymer

A-B-A-B-A-B-A-B-A-B-A-B-A


Example: PET



Block copolymer

A-A-A-B-B-B-B-B-B-B-B-A-A

Example: SIS elastomer





2. TYPES OF POLYMERS


Examples of copolymers

CROSSLINKED POLYMERS


Isobutylene isoprene rubbers



Silicone rubbers (Pt-cured)



GRAFT COPOLYMERS




2. TYPES OF POLYMERS

Polymerisation mechanism


CHAIN GROWTH

Example 1: Cationic polymerisation of "butyl elastomer"




Understanding polymerization of butyl elastomer helps to understand the formation and presence of rubber oligomers

Example 2: Radical polymerisation of polystyrene




etc, leading to polystyrene:





2. TYPES OF POLYMERS

Polymerisation mechanism


STEP GROWTH



Example: Polyaddition, polycondensation of Nylon 6,6



**SEEN AS
EXTRACTABLE/LEACHABLE**



Nylon 66
(a polyamide)

OVERVIEW

1. Definition and classification
2. Types of polymers
- 3. Properties of polymers**
4. On the origin of extractables species


3. PROPERTIES OF POLYMERS

MORPHOLOGY

AMORPHOUS POLYMERS

Because of

- Irregularities in polymer structure
- Nature of the polymer
- Cross-linking (for certain polymers)




No intermolecular bonds (e.g. Hydrogen bonds, Van der Waals forces) will lead to an alignment of the polymer chains

Examples: PS, PVC, SAN, ABS, PMMA, PC, PES

3. PROPERTIES OF POLYMERS

MORPHOLOGY


(SEMI-) CRYSTALLINE POLYMERS




Van der Waals forces (e.g. polyolefins)
Hydrogen bonds (e.g. polyamide)

Bring “alignment” in chains


Impact of stereochemistry of a polymer on physical properties



PE



Kevlar (polyamide)




Nylon 6,6 (polyamide)

3. PROPERTIES OF POLYMERS

MORPHOLOGY

AMORPHOUS VS. CRYSTALLINE




3. PROPERTIES OF POLYMERS

MORPHOLOGY


AMORPHOUS POLYMERS

Impact of **stereochemistry** of a polymer on physical properties




Isotactic

Typically semi-crystalline
(e.g. PP via Ziegler-Natta polymerisation)



Syndiotactic

(e.g. syndiotactic PS is semi-crystalline)



Atactic


Typically amorphous polymers
(e.g. atactic PS is amorphous)

3. PROPERTIES OF POLYMERS

GLASS TRANSITION TEMPERATURE (T_g)

When a polymer goes from a “glassy” state ($< T_g$) to a “rubber” state ($> T_g$)

WHAT IS RIGID PACKAGING?




3. PROPERTIES OF POLYMERS

GLASS TRANSITION TEMPERATURE (T_g)

When a polymer goes from a “glassy” state ($< T_g$) to a “rubber” state ($> T_g$)


WHAT IS FLEXIBLE PACKAGING?



3. PROPERTIES OF POLYMERS

GLASS TRANSITION TEMPERATURE (T_g)

WHICH PACKAGING?



Dr. H. Rengel, ECA Course 2006

3. PROPERTIES OF POLYMERS

GLASS TRANSITION TEMPERATURE (T_g)

Examples of T_g for different materials:

LDPE $T_g = -125^\circ\text{C}$

POM $T_g = -50^\circ\text{C}$

PP $T_g = -25^\circ\text{C}$

PBT $T_g = +70^\circ\text{C}$

PVC $T_g = +81^\circ\text{C}$ (non plasticized)

ABS $T_g = +110^\circ\text{C}$

PC $T_g = +150^\circ\text{C}$

The T_g of a material will also have an impact on the migration behavior of a material!

OVERVIEW

1. Definition and classification
2. Types of polymers
3. Properties of polymers
- 4. On the origin of extractables species**

WHAT IS IN A POLYMER?

Most Common Sources of Extractables in Polymeric Materials

Intentionally Added

- Pigments / colorants
- Clarifying agents
- Catalysts and Curing Agents
- Fillers
- Anti-oxidants
- Plasticizers
- Photostabilizers
- Slip agents
- Acid scavengers
- ...

NOT Intentionally Added

- Related to the Polymer
 - Polymer Degradation Compounds
- Related to the Polymerization Process
 - Solvent residues
 - Monomers
 - Catalysts
 - Oligomers
- Related to the additives
 - Additive degradation compounds
- Related to secondary packaging
 - Glue, Labels, Carton/Paper
- Processing Impurities
 - Lubricants, surfactants, solvents
- ...

1. INTENTIONALLY ADDED SUBSTANCES

Functionality, performance, protection, processability, cosmetic...

Blowing agents

Pigments / colorants

Antistatic agents

Metal chelators

Adhesives

Clarifying agents

Catalysts and Curing Agents

Antifogging agents

Fillers

Anti-oxidants

Plasticizers

Photostabilizers

Slip agents

Antiozonants

Coupling agents

Lubricants

Acid scavengers

Peroxides / crosslinkers

*(**blue**: coming with some examples)*


1. INTENTIONALLY ADDED SUBSTANCES

Anti-Oxidants


Function: assuring protection against thermal and oxidative degradation during processing and during shelf life of polymer

(Sterically Hindered Phenols (Primary AO) & Organic Phosphites/Phosphonates (Secondary AO) are most used)


European Pharmacopoeia lists a.o. the following anti-oxidants:




BHT




Irganox 1076




Hostanox 03




Irganox 3114



Irgafos 168



Irganox 1010



Irganox 1330

1. INTENTIONALLY ADDED SUBSTANCES

Plasticizers


Function: gives the plastic flexibility and durability

Plasticizer requirements:


- *Low water solubility (low extractibility)*
- *Stability to heat and light*
- *Low odor, taste and toxicity*




40% DEHP




Diethylhexylphthalate (DEHP)




Diethylhexylsebacate



TOTM



Diethylhexyladipate




ESBO


1. INTENTIONALLY ADDED SUBSTANCES

Photo Stabilizers


Function: protects the polymer from UV-Degradation (exposure to sunlight)



Tinuvin 328



Tinuvin 770




Tinuvin 622

1. INTENTIONALLY ADDED SUBSTANCES


Slip Agents

Function: reduce the “friction” or “film adherence”, important when producing bags from films

Low solubility in e.g. polyolefins will push slip agents to the polymer surface



Erucamide (C22)



Oleamide (C18)


Remark:

because of their specific properties, slip agents will be widely detected as Leachables!


1. INTENTIONALLY ADDED SUBSTANCES

Acid Scavengers

Function: Protects the polymer from “acid attacks” through conversion of strong acids (high degradation impact) to weak acids (low degradation impact)



E.g. in a Chlorobutyl rubber after curing




1. INTENTIONALLY ADDED SUBSTANCES


Pigments and Colorants

Function: Gives the polymer / rubber the desired color (cosmetic)


Examples: Carbon Black (PNA's!), TiO_2 (white), Fe_2O_3 (red), Pigment Green 07



Solvent Red



Solvent yellow 114





Solvent Green 03

Remark: beware of the composition of the masterbatch!

1. INTENTIONALLY ADDED SUBSTANCES

Clarifying / Nucleating Agents

Function: by controlling the crystallisation (nucleation) when cooling off polypropylene, PP becomes transparent instead of opaque



1. INTENTIONALLY ADDED SUBSTANCES

Fillers

- Function (e.g. Rubbers):

Fillers give **mechanical strength (stiffness)** to a rubber

More filler is an advantage for the gliding force for plungers, but makes stopper piercing (coring!) worse

- Aluminum silicate (clay)
- Magnesium silicate (talc)
- Silicates
- Calcium carbonate
- Carbon Black (rubbers)
- ...



1. INTENTIONALLY ADDED SUBSTANCES

Catalysts and Curing Agents

Catalyst Function: Creates the “onset” of the polymerization reaction (i.e. for addition (*cationic, anionic, radical*) polymerization)

Curing Agent Function: chemical employed in [polymer chemistry](#) that produces the toughening or hardening of [polymer](#) material by [cross-linking](#) of polymer chains via covalent bonds (thermo-setting)


Inorganic Catalysts

(Salts, oxides, complexes...)

- Titanium
- Zirkonium
- Cobalt
- Aluminum
- Iron
- Hafnium
- Platinum
- ...


Tacticity modulator

Dicyclopentylsilanediol




Example for Peroxide Curing Silicone

2,4-Dichlorobenzoyl peroxide



Dicumyl peroxide





1. INTENTIONALLY ADDED SUBSTANCES

Catalysts and Curing Agents




Catalyst Function: Creates the “onset” of the polymerization reaction (i.e. for addition (*cationic, anionic, radical*) polymerization)

Curing Agent Function: chemical employed in [polymer chemistry](#) that produces the toughening or hardening of [polymer](#) material by [cross-linking](#) of polymer chains via covalent bonds (thermo-setting)





Rubber Curing Agents



ZnO



Curing Degradation & Reaction Products



2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)



Polymer Degradation Compounds

Origin: Oxidative degradation of the polymers



(e.g. when the polymer is not properly stabilized via anti-oxidants;
e.g. "virgin" grades)

Example of polymer degradation compounds from polypropylene:




Acids






Aldehydes






Alcohols



Ketones



Polymer fragments




2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)

Solvents and monomers


Examples of Solvents




Cyclohexane




Hexane




DHN



MIBK




IPA




Toluene


Examples of Monomers




Styrene




Caprolactam



Bisphenol A




Methyl methacrylate




Isoprene



PFOA




Vinyl Acetate



Vinyl Chloride

2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)


Oligomers




2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)

Oligomers


Polyurethane




PET




PBT




Nylon 6




Nylon 6,6



Butyl Rubber



Polyester adhesive



+ oxidation, hydrolysis and degradation compounds of oligomers

Other typical oligomers from Silicone, PP, PE, adhesives,...




2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)


Polymer additive degradation compounds

Example of polymer additive degradation compounds from **Irganox 1010**:

SMALL degradation compounds




LARGE degradation compounds



2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)

Polymer additive degradation compounds

Example of polymer additive degradation compounds from **Irgafos 168**:



Remark: also, many other degradation compounds for Irgafos 168 are known

2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)

Secondary packaging for semi-permeable primary packaging


Label

- Adhesive
- Paper
- Ink
- Varnish




Typical extractable compounds:

Curing agents (e.g. Benzophenone, Irgacure 184,...)



Irgacure 184




Benzaldehyde




Cyclohexanone


Solvent residues (e.g. Toluene, acetone)




Acrylate




Methacrylate



Isobornyl acrylate



Isoborneol



Camphene


Adhesive residues (e.g. Acrylates)

Paper residues (e.g. (dehydro)abietic acids, abietates, see later)

2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)

Secondary packaging for semi-permeable primary packaging

Example GC/MS Chromatogram of a Label Extract (IPA)



2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)

Secondary packaging for semi-permeable primary packaging

Overwrap/Overpouch/Blister

(to compensate for potential lower barrier properties of the polymer)

- Multilayer system
- Aluminum as barrier layer
- Tie-layers to keep the different layers together





Typical extractable compounds:

Bislactone Compounds from Tie-layer

Residues from other layers

(depends largely on selected materials of the multilayer!!)

Bislactones:




2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)

Secondary packaging for semi-permeable primary packaging

Carton / paper

(may also come from label)



Example structures of abietic acids / abietates (& vanillin)







2. NOT INTENTIONALLY ADDED SUBSTANCES (NIAS)

Processing impurities




lubricants



detergents



solvent residues



CONCLUSION

- Know Your materials, it's composition and chemistry
- What you put in is not what will come out
- *"A polyethylene is a polyethylene"?* **NO!**
- Some of the compounds are reactive and toxic
- The complex diversity of the universe of extractables requires a broad chemical screening with a combination of techniques
- Knowledge of materials allow the broaden the analytical scope of an E/L study
- Often degradation compounds are difficult to identify
- Database assisted identification is almost a requisite for a successful screening

